



# PU MAX® TIX TRANSPARENT EXPRESS

VERY FAST, THIXOTROPIC, WATERPROOF (EN 204 D4) WOOD POLYURETHANE



- Can be used internally and externally
- Paintable
- Sandable

## CERTIFICATES & STANDARDS

Standards	
EN 204 D4	EN 204: Classification of thermoplastic wood adhesives for non-structural applications: D4

## PREPARATION

**Working Conditions:** The ambient temperature, the adhesive and the materials to be bonded should be no less than +5°C. Relative humidity of up to 65%. Level of wood humidity between 10% and 18% (max. 25%).

**Surface Requirements:** The surfaces to be bonded need to be clean, dry and free of dust. Moisten the side to which no adhesive has been applied with a damp cloth.

**Preliminary Surface Treatment:** Degrease oily types of wood with thinner. Roughen non-porous materials.

**Tools:** Sealant gun, fine-toothed glue spreader (1 mm), brush, roller, clamp or press.

## APPLICATION

**Coverage:** 5-6 m<sup>2</sup>/kg

### Directions for use:

Apply adhesive thinly and evenly to one side using a fine-toothed glue spreader (1 mm), brush or roller. Assemble joint within 2 minutes and clamp or press for at least 15 minutes. The desired pressure is 2-5 kg/cm<sup>2</sup>.

**Stains/residue:** Remove adhesive residue immediately with acetone. Dry adhesive residue can only be removed mechanically.

## PRODUCT DESCRIPTION

Fast, thixotropic, transparent, waterproof wood assembly adhesive based on polyurethane. Professional quality, conforms to standard EN 204 D4.

## FIELD OF APPLICATION

For very quick and water-resistant (EN 204 D4) mutual (surface) joining of practically all types of wood as well as joining practically all types of wood to many building materials, such as gypsum, (natural) stone, (cellular) concrete, metal, hard foam and various synthetics. Especially for bonding and repairing wood constructions and wood connections that have to meet stringent requirements. Suitable for finger joints, dovetail joints, mortise and tenon joints, dowels, springs, and more. Ideal for vertical connections. Suitable for interior and exterior applications, such as façade carpentry and sandwich panels. Also for less-fitting joints (for example, unplanned wood). D4: Interiors where flowing water or condensation are present over long periods on a regular basis. Exteriors exposed to the influences of the weather, providing effective protection for bonded wood.

Not suitable for Polyethylene (PE), polypropylene (PP), PTFE and nylon (PA).

## PROPERTIES

- Super-fast; 5 minutes
- Thixotropic; Ideal for vertical applications
- (Sea)waterproof (EN 204 D4)
- Super-strong
- Limited filling; slightly effervescent
- Solvent-free
- Temperature and all-weather resistant

Our advice is based on extensive research and practical experience. However, in view of the large variety of materials and the conditions under which our products are applied, we assume no responsibility for the results obtained and/or any damage caused by the use of the product. Nevertheless, our Service Department is always at your disposal for any advice needed.



# PU MAX® TIX TRANSPARENT EXPRESS

VERY FAST, THIXOTROPIC, WATERPROOF (EN 204 D4) WOOD  
POLYURETHANE

## TECHNICAL SPECIFICATIONS

Chemical base:	Polyurethane prepolymer
Chemicals resistance:	Good
Colour:	Transparent
Density approx.:	1.12 g/cm <sup>3</sup>
Drying/Curing time approx.*:	2 minutes
Filling capacity:	Limited
Final bond strength after:	30 minutes at 20°C
Minimum temperature resistance:	-20 °C
Maximum temperature resistance:	125 °C
Moisture resistance:	Very good
Paintability:	Good
Pressure:	2-5 kg/cm <sup>2</sup>
Solid matter approx.:	100 %
Time to press (+20°C):	15 minutes
Viscosity:	Thixotropic
Water resistance:	Very good

\* Curing time may vary depending on a.o. surface, product quantity used, humidity level and ambient temperature.

## STORAGE CONDITIONS

Store in properly sealed packaging in a dry place at between +10°C and +20°C.

Our advice is based on extensive research and practical experience. However, in view of the large variety of materials and the conditions under which our products are applied, we assume no responsibility for the results obtained and/or any damage caused by the use of the product. Nevertheless, our Service Department is always at your disposal for any advice needed.